

Fiberforge Carbon/PPS Unidirectional Blank

Representative Material Data

Material	Fiber	Carbon
	Matrix	PPS
	Laminate Orientation	[0]_n

Property	Test Standard	Units	Quantity
Fiber Content by Weight	ASTM D 3171	%	66
Areal Weight		g/m ²	225
Density	ASTM D 3173	g/cm ³	1.6
Minimum Blank Thickness		mm	0.20

Mechanical				
Property	Test Standard	Units	Longitudinal	Transverse
Tensile				
Strength	ASTM D 3039	MPa	1,780	77
Modulus	ASTM D 3039	GPa	134	9.0
Elongation at Break (calculated) ...	ASTM D 3039	%	1.3	0.9
Flexural				
Modulus (calculated)	ASTM D 790	GPa	138	9.4
Compressive				
Strength (calculated)		MPa	1,600	30
Poisson's Ratio (calculated)		—	0.27	

Thermal				
Property	Test Standard	Units	Longitudinal	Transverse
Coefficient of Thermal Expansion (calculated)	ASTM E 831	μm/m°C	-0.23	40
Processing Temperature		°C	320-350	

This data sheet lists common material, mechanical, and thermal characteristics of only one possible anisotropic tailored blank. Blanks can be made:

- thicker by adding plies
- to a desired shape, including cut-outs, to reduce scrap on final forming
- with different and/or additional ply-angles to change the anisotropic nature of the material
- with variable thickness/number of lamina.

Materials available off-the shelf or by special order.

Fiber:	Matrix:
Carbon	PA
Glass	PBT
Aramid	PEKK
	PE
	PPS
	PEEK
	PET
	TPU
	PP
	PEI
	Others

This representative data was tested, measured, or calculated using standard methods and is subject to change without notice; it should be used for informational purposes only. Fiberforge makes no warranties and assumes no liability in connection with the use of this information. This data is not intended to substitute for your own testing to determine suitability for your particular application. The data listed here should not be used to establish specification limits. Nothing in this publication is to be construed as a license to operate under or a recommendation to infringe upon any intellectual property right. Fiberforge's RELAY® Station and Tailored Blanks™ are protected by US patents #6,607,626; 6,939,423; 7,235,149, and patents pending.

FIBERFORGE®

Fiberforge
3768 Highway 82, Suite 204
Glenwood Springs, Colorado
81601 USA

phone 970.945.9377

fax 877.232.0292

fiberforge.com